

PROPIEDADES	ARENA NACIONAL ARG SAND									
	MALLA 6-12		MALLA 8-16		MALLA 10-20		MALLA 12-20		MALLA 16-30	
TAMIZADO.	4		6		8	-	8	-	12	-
	6		8		10	1	10		16	3.5
	8	9,8	10	40	12	16	12		18	30.3
	10	58,2	12	35	14	33.5	14	43,3	20	44.7
	12	26	14	20	16	36	16	32,6	25	21.3
	14	6	16	5	18	12	18	20,2	30	0.2
	16		20		20	1.5	20	3,9	40	-
	F	-	F	-	F	-	F	-	F	-
ESFERICIDAD.	0.7		0.7		0.7		0.7		0,7	
REDONDEZ	0.65		0.65		0.65		0.6		0.6	
cluster %	0		0		0		0		0	
CRUSH TEST P.S.I			2000	6,0	2000	-	2000	-	2000	-
	2000	16	2500	9,0	3000	10.2	3000	10.50	3000	10,30
			3000	14,3						



Administración y Planta Industrial

Calle 809 N°1421 Quilmes

Buenos Aires

Tel/Fax (011) 4250 5063