

PROPIEDADES		ARENA NACIONAL ARG SAND					
		MALLA 8-16		MALLA 12-20		MALLA 16-30	
TAMIZADO	8	-	8	-	12	-	
	10	40	10	-	16	-	
	12	35	12	-	18	33.8	
	14	20	14	43.3	20	44.7	
	16	5	16	32.6	25	21.3	
	18	-	18	20.2	30	0.2	
	20	-	20	3.9	40	-	
	F	-	F	-	F	-	
ESFERICIDAD.		0.7		0.7		0,7	
REDONDEZ		0.7		0.6		0.6	
cluster %		0		0		0	
CRUSH TEST	P.S.I.	2000	9.3				
			2500	8.3			
					3000	9.8	



TABLA 1

www.sandfrac.com.ar